TESC3R0V05B1X

ESD SUPPRESSOR



Features


- SMD type zinc oxide based ceramic chip
- Lead free plating termination provided good solderability characteristic
- Insulator over coat keeps excellent low and stable leakage current
- Quick response time (<1ns)
- Low clamping voltage
- High transient current capability
- Meet IEC 61000-4-2 standard
- Compact size for EIA 0603


Applications

- Application for Mother Board, Notebook, Cellular Phone, PDA, handheld devic DSC,DV,Scanner, and Set-Top Box etc.
- DSC,DV,Scanner, and Set-Top Box etc.
- Data port:Audio,Video,Keyboard,Charge etc.

Construction & Dimension







Unit: mm	0603
L	1.60±0.15
W	0.80±0.1
Т	0.80±0.1
С	0.30±0.20

Part ratings and characteristics

	Working voltage		Varistor voltage	Clamping Voltage	Capacitance	Peak current	Transient energy
Symbol	V _{RMS}	V _{DC}	Vv	Vc	Ср	İmax	Wmax
11	Volts	Volts	Volts	Volts	pF	Amps	Joules
Units	(Max.)	(Max.)		(Max.)	(Typical)	(Max.)	(Max.)
Test Condition		< 10 μΑ	1mA DC	1A 8/20μs	1MHz	8/20μs	10/1000μs
TESC3R0V05B1X	-	5	45 ~ 65	135	3	-	-

 V_{RMS} – Maximum AC operating voltage the varistor can maintain and not exceed10 μ A leakage current

- V_{DC} Maximum DC operating voltage the varistor can maintain and not exceed 10 μ A leakage current
- V_V Voltage across the device measured at 1mA DC current. EquiValent to Vb, "Breakdown Voltage".
- Cp Device capacitance measured with zero volt bias 1 ms at 1MHz.
- $\label{eq:continuous} Vc-Maximum\ peak\ voltage\ across\ the\ varistor\ measured\ at\ 8/20us\ waveform\ and\ 1A\ pulse\ current$
- i_{max} Maximum peak current which may be applied with 8/20us waveform without device failure
- W_{max} Maximum energy that may be dissipated with the 10/1000us waveform without device failure.

General electrical specifications

General technical data

Operating temperature	-40 +85°C
Storage temperature (on board)	-40 +85℃
Response time	<1 ns
Solderability	245±5°C, 5+0/ -0.5sec
Solder leach resistance	260±5°C,10 ±1sec

Environmental Specifications

Characteristics	Specifications	Test condition		
Bias humidity	$\Delta V_V/V_V \le \pm 10\%$	90%RH, 40℃, Working voltage, 1000 hours		
Thermal shock	$\Delta V_V/V_V \le \pm 10\%$	-40°C to 85°C, 30 min. Cycle, 5 cycles		
Full load	AV /V < ±100/	Working voltage 95°C 1000 hours		
voltage	$\Delta V_V/V_V \le \pm 10\%$	Working voltage, 85°C, 1000 hours		


Storage Condition with package

Storage Temperature: 5 to 40°C

Relative Humidity: to 65% Storage Time: 12 months max


Taping Package and Label Marking

Carrier tape dimensions



) _A •
Α	В	С	D	Е	F L	W
8.00±	3.50±	1.75±	2.00±	4.00±	1.50± 1.90±	
0.30	0.05	0.10	0.05	0.10	0.10 0.15	0.15

Taping reel dimensions



Α	178.0±2.0
В	2.0±0.5
С	13.0±0.5
D	21.0±0.8
E	62.0±1.5
F	9.0±0.5
G	13.0±1.0

Taping specifications

There shall be the portion having no product in both the head and the end of taping, and there shall be the cover tape in the head of taping.

Quantity of products in the taping package


- (1) Standard quantity: 4000pcs/Reel for MLVS 0603 Lead Free series
- (2) Shipping quantity is a multiple of standard quantity.

Precautions for Handling

Solder cream in reflow soldering

Refer to the recommendable land pattern as printing mask pattern for solder cream.

- (1) Print solder in a thickness of 150 to 200 μ m.
- (2) Dimensions: millimeters (inches)



Precaution for handling of substrate

Do not exceed to bend the board after soldering this product extremely. (Reference examples)

- Mounting place must be as far as possible from the position, which is close to the break line of board, or on the line of large holes of board.
- Do not bend extremely the board, in mounting another component.

 If necessary, use back-up pin (support pin) to prevent from bending extremely.
- Do not break the board by hand. We recommend using the machine or the jig to break it.

Precaution for soldering1


Note that rapid heating, rapid cooling or local heating will easily damage this product.

Do not give heat shock over 100°C in the process of soldering. We recommend taking preheating and gradual cooling.

Recommendable reflow soldering

*According to J-STD-020C

Profile Feature	Pb-Free Assembly
Average Ramp-Up Rate	3° C/second max.
(Tsmax to Tp)	
Preheat	
– Temperature Min (Tsmin)	150°C
– Temperature Max (Tsmax)	200°C
– Time (tsmin to tsmax)	60-180 seconds
Time maintained above:	
– Temperature (TL)	217°C
– Time (tL)	60-150 seconds
Peak/Classification Temperature (Tp)	260°C
Time within 5 °C of actual Peak	
Temperature (tp)	20-40 seconds
Ramp-Down Rate	6°C/second max.
Time 25 °C to Peak Temperature	8 minutes max.



Soldering gun procedure

Note the follows, in case of using solder gun for replacement.

- (1) The tip temperature must be less than 350°C for the period within 3 seconds by using soldering gun less than 30W.
- (2) The soldering gun tip shall not touch this product directly.

Soldering volume

Note that excess of soldering volume will easily get crack the body of this product.

Contant Information

SHENZHEN TOP-FLIGHT TECHNOLOGY CO.,LTD

4th Floor, C Building, Quansen Industrial Park , Bulong Road, Longhua New District, Shenzhen Tel: 86-755-82908191 Fax: 86-755-82908701 Email:kang@topleve.com

Website: http://www.topleve.com